

marglass V1035

NON FLAMMABLE FABRIC



EN Flame retardant texturized FIBERGLASS fabric with vermiculite coating
 ES Tejido ignífugo de fibra de vidrio tipo Eglass texturizado con tratamiento de vermiculita



Technical Data Sheet

Composition	72% E-glass 28% Vermiculite
Base	Fiberglass
Working side treatment	Vermiculite
Reverse side treatment	Vermiculite
Weave	Plain

Physical Properties

	Metric	US
Weight	1035 gr/m ² ±5%	30 oz/yd ² ±5%
Thickness	1,3 mm	0,051 in
Width <i>(contact us for especial widths)</i>	100 cm ±2%	39 in
Roll lenght	50 mt	55 yd

Thermal Properties

	Metric	US
Continous temp	800 °C	1472 °F
Peak temp	1000 °C	1832 °F

Common Applications

- Flame barrier
- Thermal barrier
- Vertical curtains
- Fire blankets
- Welding blanket

Main Features



Flame Resistant



Abrasion resistant



Thermal resistant

Technical Specs

	Results	Standard
Limited Flame Spread	A1 - A2	ISO 15025
Tensile Strenght	Warp > 4500 N ±10% Weft > 2500 N ±10%	ISO 4606

Maintenance Information



What is the Metrik?